

HOT DIP GALVANIZED STEEL STRIP "BAZIT"®



PRODUCTION STANDARDS:

- Hot dip galvanized steel strip according to SR EN 62561-2/2018
- Steel grade S235JR, according to SR EN 10025-2/2004; SR EN 10111/2008
- Checking of adherence according to SR EN 50164-2/2009
- Checking of Zinc layer according to: SR EN ISO 1461/2002; SR EN ISO 1460/2002; SR EN 2178/1998
- Tolerance of size according to SR EN 10051+A1/2000
- Zinc layer Z 300 and Z 500 according to the customer request
- Delivery way: in coils
- Coils weight - 50 kg or as per customer request
- Packs of 1 to/pallet or as per customer request
- Rounded edges.

TECHNICAL DETAILS

„BAZIT®” hot dip galvanized steel strip
Z 500 = minim 70 microns or Z 300 = minim 42 microns

Sizes	Kg/ml	Lenght (m) approx.	Weight (kg) ± 1 kg
40x4	1,30	38	50
30x3,5	0,82	61	50
30x3	0,74	67	50
60x5	2,36	21	50
50x5	2,00	25	50
40x5	1,60	30	50
50x4	1,60	30	50
30x4	1,00	51	50
25x4	0,80	61	50
40x3	1,00	51	50
25x3	0,60	81	50
20x3	0,50	100	50
30x2	0,47	107	50
20x2	0,32	156	50

CERTIFICATIONS/ AGREEMENTS:

- TÜV: *Quality, Environment, Occupational Health*
- AFER
- ICECON

